



HSM Wire International, Inc

Ph: 330-244-8501 Fax: 330-244-8561

www.hsmwire.com

Ni Cr A - Increase in Resistance with Temperature

°F	68	200	400	600	800	1000	1200	1400	1600	1800	2000
°C	20	93	204	315	427	538	649	760	871	982	1093
% Increase	0	0.8	2	3.3	4.8	6.3	5.8	5.1	5.2	5.6	6

Ni Cr C - Increase in Resistance with Temperature

°F	68	200	400	600	800	1000	1200	1400	1600	1800
°C	20	93	204	315	427	538	649	760	871	982
% Increase	0	1.7	3.5	5.2	6.9	8.6	9.2	9.8	10.2	10.5

*To be used as a guideline only.

Copyright © 2014 HSM Wire International

R.1.06.04.2014